



Product Information

Delfleet® Evolution

F3434

– F3434 Epoxy Accelerator

Products

Delfleet Epoxy Accelerator F3434

Delfleet Epoxy Primer F3955

Product Description

Delfleet Epoxy Accelerator is an additive used to assist the drying of Delfleet Epoxy products only, when the temperature is below 15°C.

Usage Guide

The accelerator should be added to the mixed primer when ready-to-spray stage in the proportion of either :

- 3% by weight
- Or 30 gm per litre
- Or 33 ml per litre

The pot life is 4 hours.


PERFORMANCE & LIMITATIONS



1. Care should be taken not to use more than 3% by weight (30 gm per litre or 33 ml per litre) otherwise the drying performance and durability may be affected.
2. Do not use in 2K Primer F3975/F3988
3. DO NOT USE F3431 in Deltron BC
4. The addition of accelerator reduces the potlife of the mixed paint

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with cleaning solvent or thinner.



HEALTH & SAFETY

For comprehensive Health, Safety and Environmental advice, please refer to relevant Material Safety Data Sheets and Product Can labels. Use the recommended safety equipment.

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development. Drying times quoted are average times at 20°C. Film thickness, humidity and shop temperature can all affect drying times.



PPG INDUSTRIES
AUSTRALIA PTY LIMITED
McNaughton Road
Clayton VIC Australia 3168
Tel: 13 24 24
Fax: 1800 800 819

PPG INDUSTRIES NZ
LIMITED
5 Vestey Drive Mt. Wellington
Auckland New Zealand
Tel: 0800 320 320
Fax: 0800 320 322