



ENVIROBASE[®]
HIGH PERFORMANCE

PPG's advanced waterborne basecoat system
ENGINEERED FOR EXCELLENCE



LVA-600

LOW VOC WB MULTI-STRIPE ACTIVATOR

PRODUCTS

Envirobase HP mixed colour

LOW VOC LOW VOC WB Multi-Stripe Activator

Envirobase Thinner

LVA-600

T494

PRODUCT DESCRIPTION

LVA-600 LOW VOC WB Multi-Stripe Activator is used with Envirobase HP mixed colours where a multistripe finish is required such as: Two tone vehicles on cars or adding stripes to commercial transport vehicles.

When LVA-600 LOW VOC WB Multi-Stripe Activator is mixed with an Envirobase HP mixed colour it will allow the basecoat surface to be masked on leaving no visible masking lines.

SUITABLE SUBSTRATES


Refer to Envirobase HP Datasheet

SUBSTRATE PREPARATION

Refer to Envirobase HP Datasheet

MIXING RATIO BY VOLUME

Note: Hand shake LVA-600 before use



PRODUCT

Envirobase HP mixed colour

LVA-600 LOW VOC WB Multi-Stripe Activator

Thinner T494

PARTS


3 PARTS BY VOLUME

1 PART BY VOLUME

10-30%


Choose Thinner according to application temperature and repair area size

POTLIFE @ 20°C



48 Hours when basecoat is Activated

SPRAY VISCOSITY @ 20°C



15 - 18 Seconds (DIN4)
Dependant on % of thinner level chosen

SPRAYGUN SETUP


Refer to Envirobase HP Datasheet

NUMBER OF COATS & FLASH OFF



2-3 Coats

Apply 2-3 even medium coats



Flash off between coats
Flash off @ 20°C before masking

Use air mover/blower until matt
30 minutes


TOPCOATING

Apply an approved Envirobase HP clearcoat within 24 hours of applying the basecoat.

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with Envirobase HP cleaning solvent.

HEALTH AND SAFETY



Please refer to Material Safety Data Sheets for full Health and Safety details and product can labels.

Goggles must be worn when mixing and using to prevent accidental splashing into the eye. If contact occurs with eyes give prolonged irrigation with water and get medical attention immediately.

Good ventilation and extraction must be provided in the working environment.

Wear suitable protective equipment to prevent skin contact with this material.

When spraying this product the operator (and persons in vicinity) must wear suitable air-fed breathing apparatus.

Do not smoke whilst using this material.

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times.



PPG INDUSTRIES AUSTRALIA PTY LIMITED

McNaughton Road

Clayton VIC Australia 3168

Tel: 13 2424

Fax: 1800 800 819

PPG INDUSTRIES NEW ZEALAND PTY LIMITED

5 Vestey Drive Mt. Wellington

Auckland New Zealand

Tel: 0800 320 320

Fax: 0800 320 322