



Product Information

SU4909


Anti-Silicone additive

Product Description

SU4909 Anti-Silicone Additive has been developed to be used in 2 Pack Topcoats when silicone cratering (fisheyes) occurs during the painting process.

Application Guide

Mixing Ratio



Add 2% to a maximum of 5% (by volume) of Anti-Silicone Additive to the catalysed Topcoat.

Thoroughly stir into mixed paint before application.

Application



If, during spraying, silicone craters appear, cease application and add Anti-Silicone Additive to catalysed material. Ensure Anti-Silicone Additive is thoroughly mixed in before continuing application.


Overcoat with



When Anti-Silicone Additive has been used, all subsequent coats must also contain Anti-Silicone Additive added at the same level. Failure to add Anti-Silicone Additive to subsequent coats will lead to poor flow and appearance. Adhesion may also be affected.

Performance Guidelines

1. Anti-Silicone Additive should only be used when silicone cratering (fisheyes) appear.
 2. For use with 2 Pack Topcoats.
 3. When mixing and handling Anti-Silicone Additive avoid contact with other materials. Thoroughly clean and wipe all equipment after using Anti-Silicone Additive. Dispose of solvent used to clean equipment immediately to avoid further contamination. Dispose of all rags used with Anti-Silicone Additive to avoid further contamination.
-



HEALTH AND SAFETY

Health and Safety

Please refer to Material Safety Data Sheets for full Health and Safety details and product can labels.

- Goggles must be worn when mixing and using to prevent accidental splashing into the eye. If contact occurs with eyes give prolonged irrigation with water and get medical attention immediately.
- Good ventilation and extraction must be provided in the working environment.
- Wear suitable protective equipment to prevent skin contact with this material.
- When spraying this product the operator (and persons in vicinity) must wear suitable breathing apparatus.
- Do not smoke whilst using this material.

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times.



**PPG INDUSTRIES AUSTRALIA
PTY LIMITED
McNaughton Road
Clayton VIC Australia 3168
Tel: 13 2424
Fax: 1800 800 819**

**PPG INDUSTRIES NEW ZEALAND
PTY LIMITED
5 Vestey Drive Mt. Wellington
Auckland New Zealand
Tel: 0800 320 320
Fax: 0800 320 322**