



Product Information

METAL CONDITIONER *SX520*

Products

SX520 – Metal Conditioner

Product Description

SX520 Metal Conditioner is a phosphoric based conditioner that will deposit a uniform layer of zinc phosphate on properly prepared galvanised and steel surfaces.

SX520 is a hand applied coating chemical formulated to provide improved paint adhesion and corrosion resistance. It provides a non-metallic, non-conductive, pale green conversion coating on galvanised and steel surfaces which enhances the paint adhesion and corrosion resistance of the painted parts.

Application Guide

This product is for automotive refinish use on galvanised and steel substrates. It should not be used for aluminium. Please read the precautionary information on the label and MSDS before use.

Application of SX520 Metal Conditioner

Apply un-diluted from the container using a brush or an abrasive pad.

Always use an abrasive pad for Galvanised or Galvaneal.

Keep solutions, brushes, pads and rags clean.

Contact Time

Allow a contact time of 1 to 2 minutes only.

Do not allow the metal surface to dry off before rinsing. (Rewet with SX520 if necessary).


Rinsing and Drying

Rinse thoroughly with clean water. Dry with clean rags or blow off with compressed air. Do not solvent wipe.

Theoretical Coverage

1 litre of SX520 will treat approximately 20 m² of metal surface.

Overcoating



Prime the metal surface with a suitable Epoxy Primer within 4 hours of the pre-treatment process.

Health and Safety

Please refer to Material Safety Data Sheet for full Health and Safety details and storage regulations.

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times.



**PPG INDUSTRIES AUSTRALIA
PTY LIMITED
McNaughton Road
Clayton VIC Australia 3168
Tel: 13 2424
Fax: 1800 800 819**

**PPG INDUSTRIES NEW ZEALAND
PTY LIMITED
5 Vestey Drive Mt. Wellington
Auckland New Zealand
Tel: 0800 320 320
Fax: 0800 320 322**